

CURECON W

Water dispersed Type 1-D, Class B resin curing compound

DESCRIPTION

Curecon W is a Type 1-D, Class B, water based resin curing compound used to retain moisture in concrete for effective curing. Used for all concrete but specifically designed for use in mass concrete structures such as roadwork, bridgework and runways.

Curecon W can also be supplied as Type 2 or Type 3 product, where site conditions dictate the use of either of these types.

Curecon W is certified to comply with Australian Standard AS 3799.

ADVANTAGES

- Increases concrete strength and dusting resistance
- Reduces surface shrinkage and cracking by eliminating moisture loss from exposed surfaces.
- Eliminates the need for damp hessian, sand or polythene
- Rapid film formation
- Tack free when dry
- Non toxic
- Complies with Green Star – Office Design V3 IEQ-13
- Volatile ingredients comply with air pollution requirements of photo-reactive compounds
- Non-flammable/non dangerous goods classification

DESIGN CRITERIA

The coating should be applied at a coverage rate of 5m²/litre.

To achieve the correct curing properties and moisture retention according to Australian Standard and various road construction specifications, Curecon W must be applied at the above stated coverage rates.

Curecon W contains a fugitive dye to ensure even coverage is attained. This dye evaporates after a short period of time leaving the dried Curecon W as a transparent film.

TYPICAL PROPERTIES

Drying time on concrete	Approx. 3 hours at 25°C and 50% RH
Viscosity	>0.05 Pa
Specific Gravity	0.95-1.0
Flash point	Not Applicable
Colour	Light green liquid
Coverage	5m ² /litre using a spray applicator-do not brush
Application equipment	low pressure spray (preferred) or soft 10-15 mm nap roller
Thinning	Nil - use as supplied
Clean-up	Water when wet. Kerosene, fuel or solvent525 (allows re-emulsification with water) when dry

APPLICATION INSTRUCTIONS

Use Curecon W as supplied – do not dilute.

The coating should be evenly sprayed onto the surface over the freshly laid concrete as soon as possible after final trowelling. Ideally Curecon W should be applied as soon as the surface bleed water has evaporated.

In all cases Curecon W should be applied at a coverage rate not less than 5m² per litre.

Note: Aliphatic alcohol preparations used in the finishing process of the concrete surface will not interfere with the drying or bond characteristics of Curecon W.

COMPATABILITY

Curecon W is compatible with many hydrocarbon solvent-based primers and is suitable for use on concrete roads which will be subject to line marking. However compatibility tests should be undertaken and confirmed by testing in each and every case.

Curecon W will darken slightly with age and UV exposure. In time the coating will degrade, allowing the unhindered application of other toppings/treatments.

The life of Curecon W will depend on the degree of exposure to weathering that the product experiences. The coating is designed to break

down on exposure to weathering influences. Continual exposure to UV light and the effects of weather is needed to ensure this process takes place. It is expected that under these conditions the process will take up to 12 weeks for the Curecon W coating to fully break down.

CLEAN UP

Tools and equipment can be cleaned with water while Curecon W is wet.

Dried Curecon W can be removed using proprietary paint strippers, Solvent 525 or by mechanical means.

ESTIMATING

Curecon W is applied at the rate of 5m² per litre (0.2 litres per m²). Note that surface texture of the finished concrete can affect the apparent coverage rate of the applied coating of Curecon W.

Curecon W is supplied in 20 litre cubes, 200 litre drums and 1,000 litre IBC containers, or in bulk.

PRECAUTIONS

Do not dilute Curecon W. Use as supplied

Ensure that Curecon W is thoroughly mixed before application commences. Regular mixing of the material during application is recommended.

Do not allow Curecon W to freeze.

Where high or low temperatures are likely to be encountered, Type 2 or Type 3 versions of Curecon W may be required. Contact ITLS Technical Services for advice in these circumstances

STORAGE

Curecon W should be stored in the original unopened containers in cool, dry conditions. Store away from sources of heat or naked flame. Do not allow Curecon W to freeze.

Curecon W should be used within 12 months of date of manufacture. If the product has been stored for more than 6 months, particular care should be taken to ensure the product is thoroughly mixed before use.

HEALTH AND SAFETY

Curecon W is non-toxic.

When applying the product, always use suitable cartridge masks, avoid skin and eye contact.

Avoid breathing spray mist during application.

For more detailed information, please read the MSDS for this product.

TECHNICAL SUPPORT

ITLS manufactures a comprehensive range of high quality, high performance construction products. In addition, ITLS offers technical support and on-site advice to specifiers, end users and contractors.

Please contact your ITLS sales representative or ITLS Head Office for this service

ALLIED PRODUCTS

ITLS manufactures a broad range of products under the Aftek brand, which are used in the construction industry and in manufacturing, including:

Grouts
Coatings
Admixtures
Adhesives
Sealants
Floor Toppings
Floor Levelling Compounds
Concrete Repair
Concrete Curing

The information and any recommendations relating to the application and end-use of all ITLS products are provided in good faith based on ITLS's knowledge and experience of the products. In applications, the differences in materials, and variances of substrates and actual site conditions can vary such that no warranty in respect of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be taken as inferred either from this information, or from any written recommendations, or from any other advice offered by ITLS. The proprietary rights of third parties must be observed. All orders are accepted subject to our sale terms and conditions. All users should always refer to the most recent and up to date issue of the Technical Data Sheet for the product concerned, which is available on request. It is recommended that products should always be properly stored, handled and applied under tested and recommended conditions.

PLEASE CONSULT OUR TECHNICAL DEPARTMENT FOR FURTHER INFORMATION.



For Further Information

250 Princes Highway
Dandenong Vic 3175
Phone: 1800 651 631 Fax: 1800 672 270
(ABN 41 139 650 883)

Product:	Curecon W
Issue Date:	November 2010
Issue No:	2
Division:	Construction
Total Pages:	2