

MasterBrace® Fibre

The MasterBrace Fibre System is a Fibre Reinforced Polymer (FRP) system for structural strengthening of concrete and timber structures. The system comprises of Carbon, Aramid or Glass fibre sheeting enveloped in a site applied MasterBrace Saturant epoxy

DESCRIPTION

MasterBrace Fibre sheet reinforcement materials are enveloped in **MasterBrace 4500** resin to yield a range of high performance composites with many features.

RECOMMENDED USES

- Flexural and shear strengthening elements that may not be planar (flat)
- Increasing compressive strength via axial confinement of columns
- Seismic retrofitting of columns and piles for earthquake resistance
- Enhancement of fatigue resistance under repetitive loading conditions
- Walls, beams, slabs, silos, chimneys, tanks, pipes, tunnels, piles etc

FEATURES AND BENEFITS

MasterBrace Fibres (in general)

- Lightweight and durable Easy to apply and noncorroding
- High strength to thickness ratio does not interfere with widths or thicknesses of members nonobtrusive

MasterBrace Carbon Fibre

 Increased strength- for Flexure, Shear, Confinement & Fatigue enhancement and end anchoring of MasterBrace Laminates

MasterBrace Aramid Fibre

 Increased strength for -Impact resistance or Blast (Explosion) resistanc

PROPERTIES

MasterBrace FIB 300/50 CFS

Fiber Areal Weight	300g/m ²
Fabric Design Thickness	0.166mm
Fibre Tensile Strength	4900 MPa
Fibre Tensile E-modulus	230 GPa
Elongation at break	2.1%
Fabric length/roll	100m
Fabric width	50cm

MasterBrace FIB 450/50 CFS

Fiber Areal Weight	450g/m ²
Fabric Design Thickness	0.255mm
Fibre Tensile Strength	4900 MPa
Fibre Tensile E-modulus	230 GPa
Elongation at break	2.1%
Fabric length/roll	50m
Fabric width	50cm

MasterBrace FIB 415/50 AFS

Fiber Areal Weight	415g/m ²
Fabric Design Thickness	0.288mm
Fibre Strength	3200 MPa (Kevlar 49)
Fibre Stiffness	120 GPa (Kevlar 49)
Fibre Tensile Strength	2060 MPa
Fibre E=modulus	118 GPa
Elongation at break	2.4%
Fabric length/roll	50m
Fabric width	30cm

APPLICATION

For detailed instructions, refer to the "MasterBrace Application Guidelines for FRP Fabric (Sheet) Materials" document.

Fibres must be completely saturated in resin. Carry out work only under appropriate environmental conditions.

ESTIMATING DATA

Refer to specific material Performance Data tables for details.

PACKAGING

Refer to specific material Performance Data tables for details.

SHELF LIFE

MasterBrace Fibre has a shelf life of 36 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall





MasterBrace® Fibre

ID#MasterBrace Fibres- ANZ -v2-0515

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Australia Ltd
ABN 62008437867
Construction Chemicals Division
11 Stanton Road Seven Hills, NSW 2147

Sales Offices: Sydney, Brisbane, Melbourne, Adelaide,

Sydney, Brisbane, Melbourne, Adelaide Perth

Freecall: 1300 227 300

BASF Emergency Advice:

1800 803 440 within Australia (24hr) 0800 944 955 within New Zealand

BASF New Zealand Ltd BASF WEB SITES 45 William Pickering Drive, Albany, Auckland, Phone: 0800 334 877
www.master-builders-solutions.basf.co.nz
www.master-builders-solutions.basf.co.nz